

Art-Nr. M101639

Bleche

Technische Daten

Legierungs-/Werkstoffnorm EN AW-5754 (AlMg3)

Werkstoff Aluminium
 Zustand H111 (weich)
 Ausführung Normalqualität
 Zugfestigkeit Rm 190-240 MPa
 Dehngrenze Rp 0.2 min. 80 MPa
 Bruchdehnung A50 12 - 18 %
 Brinellhärte ca. 52 HB


Klassifikation

eClass 10.1 35-02-05-01

eClass 11.0 35-07-01-01

eClass 12.0 35-07-01-01

UNSPSC 11.2 30102506



Art-Nr.	t mm	a mm	b mm	kg/Tfl. kg
101513	1.5	1000	2000	8.01
103739	2.0	1500	3000	24.03
104241	3.0	1500	3000	36.45
104327	4.0	1500	3000	48.06
101467	5.0	1500	3000	60.75
101469	6.0	1500	3000	72.9

Preise exkl. Verpackungskosten

